



Vipond's Paints Pty Ltd

2 Norris Street North Coburg 3058
Phone (03) 93504188 Fax (03) 93542732
Email vic@viponds.com.au

www.viponds.com.au

PRODUCT INFORMATION

FEATURE GLOSS ENAMEL

Description

A ready to use alkyd enamel formulated to give high opacity and a full gloss durable finish in a variety of accent colours. This product utilises the most light fast pigments that are available to obtain optimum durability. It is heavy bodied to allow high film build and good flow.

Use

On all exterior and interior surfaces in the home, commercial and industrial premises. Ideal for signwriting, background, feature and general work.

Application

Thoroughly stir the paint and apply with brush, roller or spray.

Surface Preparation

To ensure maximum durability and gloss level, surface preparation is most important.

Timber - Exterior - Prepare timber and apply Vipond's Pink Primer followed by Vipond's High Cover Undercoat. Interior - Sand and fill and apply Viponds High Cover Undercoat or Vipond's Acrylic Easy Sand Undercoat.

Iron and steel - Clean surface of dirt, oil and grease and remove any rust then apply Vipond's Zinc Phosphate Metal Primer.

Galvanised Iron and Aluminium – Remove oil and grease with mineral turpentine and then apply Viponds Acrylic Metal primer.

Brick, Cement, Masonary, Plaster - Prepare and apply Vipond's Acrylic Concrete and Masonry Sealer followed by a coat of Vipond's Quick Dry Undercoat.

Previously Painted – Scrape off all loose and flaking paint and sand glossy surfaces. Wash down with sugar soap, spot prime bare areas with appropriate primer then apply Vipond's Quick Dry Undercoat.

Drying

Under normal drying conditions (15°C and low humidity) it is touch dry within 4 hours and through dry within 24 hours. Recoat after 24 hours.

Cleaning and Thinning

Mineral Turpentine

Coverage

Approximately 16 square metres per litre per coat.

Pack Size

250 mls, 500 mls, 1 litre and 4 litre

Colours

Colour card and customer specifications.

Revised July 2005