



S-PRINT

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	85 microns	non adhesive polyester	REACH n° 1907/2006/EU   OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 1400240.O CENTROCOT

APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	Blade	Pressure	Speed	Time : Textile Weight	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends, Spandex	45°	60 gf	15 cm/sec	≤ 160g/m²=5sec > 160g/m²=10sec	120°C (248°F)	Medium (2,5/3,5 bar)	hot

- Print using **SOFT PRINT COLOR MATT** profile and cut the material
- Allow the print to dry at least 15 minutes
- Weed excess material
- Remove the print from the carrier with the help of TTD Easy/Advanced
- Place the decoration on the fabric
- Heat apply at the conditions shown above
- Peel TTD Easy/Advanced while hot

PRODUCT HIGHLIGHTS

- Soft touch
- Low transfer temperature
- Short transfer time

NOTE: Given the large number of inks and printers, we highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	YES best inside- out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com
For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID: 9105027958

