

TexBannerSol Xtrem white 170

— matt 3269 - 170 g/m²

TexBannerSol is an extremely white, universal 100% synthetic non-woven banner with a high quality waterfast inkjet coating. The first class look and feel of this material is supported by its unbeatable cost : performance ratio.

Applications

- Indoor signs
- Indoor adverts
- Pop-up / Roll-up Displays
- Outdoor signage

Advantages

- Light, flexible banner with high tensile strength and tear resistance
- High opacity
- Good flatness
- Can be stapled, sewn or used with grommets
- High water-resistance
- Bright and vivid colours
- Good cost : performance ratio
- PVC-free and recyclable

TexBannerSol Xtrem white 170

— matt 3269 - 170 g/m²

List of Printers

Printer	Ink	Quality
Hewlett Packard DJ L65500 Latex ink	Inkjet with IR / Latex Ink	Excellent
Hewlett Packard DJ L25500 / 26500 / 28500 - Latex 260 / 280	Inkjet with IR / Latex Ink	Excellent
Hewlett Packard Scitex LX 600	Inkjet with IR / Latex Ink	Excellent
Hewlett Packard Scitex LX 800 / LX 820 / LX 850	Inkjet with IR / Latex Ink	Excellent
Epson Stylus Pro GS6000 UltraChrome GS	Inkjet with Eco Solvent	Excellent
Epson SureColor SC-30600 / 50600 / 70600	Inkjet with Eco Solvent	Excellent
Roland SolJet SJ540 / SC540 SJ 740 / SC740	Inkjet with Eco Solvent	Excellent
Roland SC-500 Permasol S	Inkjet with Solvent Ink	Excellent
Roland VersaCAMM SP-300i / SP-540i	Inkjet with Eco Solvent	Excellent
Roland VersaCAMM VP-300i / VP-540i	Inkjet with Eco Solvent	Excellent
Roland VS 540 / VS 640	Inkjet with Eco Solvent	Excellent
Roland CJV 30	Inkjet with Eco Solvent	Excellent
Roland SolJET PRO4 XR-640	Inkjet with Solvent Ink	Excellent
Océ CS9360 / CS935	Inkjet with Eco Solvent	Excellent
Hewlett Packard Latex 310 / 330 / 360 / 3000	Inkjet with IR / Latex Ink	Good
Océ Colorwave 600 / 650 / 700	Océ Crystal Point Technology - Solid Ink	Good
Last update: 30.03.2016		

TexBannerSol Xtrem white 170

— matt 3269 - 170 g/m²

Physical Properties

Weight (Total) [gsm]	170	ISO 536
Thickness (total) [microns]	370	ISO 534
Whiteness (CIE, D65)	135	ISO 11475
Chromaticity (D65 / 10°)	L* 95.0, a* 4.0, b* -10.0	DIN 6174
Opacity [%]	> 90	ISO 2471

General tips & storage

For quality reasons the media should be stored and converted under conditions of 30-65% relative humidity at a temperature of 10-30°C / 50-86°F.

Recommended profile for HP L360:

HP Professional Gloss Photo Paper, 16 passes

The values provided on this datasheet are only for orientation.

Before using our media please check its compatibility for your printer and intended application. Technical specifications are subject to change, therefore we do not take responsibility for any misprints resulting from technically modified inks and/or printers.